

DAS-FR

data sheet

Design	DAS-FR	
Composition	49%PP 21%MA 16%CO 14%PES	
Width	140	
Linear Weight	623 gr/lm $\pm$ 5%	
Seam slippage resistance EN ISO 13936/2	WARP	3
	WEFT	3
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	32.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	5	
Assessment of ignitability	Cigarette test / Match test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Lightfastness EN ISO 105-B02	>6	
Colour fastness to rubbing EN ISO 105-X12	DRY	5
	WET	5
Dimensional change in domestic washing and drying EN ISO 3759 / EN ISO 6330 / EN ISO 5077	WARP	-1,5%
	WEFT	-1,5%
Cleaning	   	
Environment	• Oeko-Tex Certified Yarn • 100% free of heavy metals and halogens • ISO 14001 certified • Resource-efficient manufacturing	

