

MIRO-FR

data sheet

Design	MIRO-FR	
Composition	38%PP 27%PES 19%MA 16%CO	
Width	140	
Linear Weight	670 gr/lm $\pm$ 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	35.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	5	
Lightfastness EN ISO 105-B02	5-6	
Cleaning	   	