

**Test report Textile Pilling
NS-EN ISO 12945-2 :2000**

Client Crevin,s.a. Pol. Ind. Santa Margarita I C/ Llobregat, 21 08223 TERRASSA Spania		Product GALAXY Product specification - tested object	
Client's reference Pep Margarit		R-no. R16198	
Date 15.12.2017	Date of receipt, tested object 05.12.2017	Test completed date 15.12.2017	Rev. no. / Rev. date 1/15.02.2018

Manufacturer: Crevin

Composition: 58% WO 20% PP 12% PES 7% MA 5% CO

Loading Mass : 415 g Type felt: Woven

The samples are conditioned at 20 degrees C and 65 % relative humidity for 18 hours

Numerical assessment of pilling is done on a Martindale abrasion tester according to NS-EN ISO 12945-2. The samples are given a multi-directional movement and are rubbed against fabric of 100% wool (SM 25). 3 samples are used and they are examined on 500, 1000, 2000 and 5000 rubs. The average on each stage is reported as the pilling grade.

The samples are examined on a scale from 1-5 where 5 is best. Examined by 1 person.

Results:
2000 Cycles: 5
7000 Cycles: 5

Comments:

Deviations from test standards: 2000,7000 cycles



Bård Vestre
Manager