crevin

CHANEL

data sheet

Design		CHANEL
Composition		48%PES 32%PP 20%CO
Width		140
Linear Weight		695 gr/lm ± 5%
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	26.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2		4-5
Lightfastness EN ISO 105-B02		5-6
Cleaning		30

Crevin s.a. All rights reserved.
Unauthorized copying is prohibited.