


CHIC

data sheet

Design	CHIC	
Composition	53%PES 34%PP 13%CO	
Width	140	
Linear Weight	750 gr/lm \pm 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	60.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Lightfastness EN ISO 105-B02	5-6	
Cleaning		

efficiency

