

FEATURES

ARTICLE: ANIMA						IN-00491/2017-B-1	
COMPOSITION: 85%PES 15%CO							
WIDTH: 140	+4cm.	WEIGHT: 530	Gr/m2. ±5%	742	gr/ml.±5%	WARP	WEFT
STATISTICAL NUMBER: 58013600 USA : 5801360020							
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)						3	2.8
ABRASION RESISTANCE (Fully worn off) EN ISO 12947-2:1998						100.000	
ABRASION RESISTANCE (Change of aspect: 3000 cycles) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)						3-4	
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)						4-5	
ASSESSMENT OF IGNITABILITY BS 5852 Source 0 // EN 1021-1:2006 (cigarette test)						PASSED	
BS 5852 Source 1 // EN 1021-2:2006 (match test)						---	
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)						5-6	
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 Degradation and loss of colour on grey scale (From 1 worst to 5 best)				DRY		---	
				WET		---	
COLOUR FASTNESS TO DOMESTIC AMD COMERCIAL LAUNDERING (30°) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)						---	
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008						-1%	-2%
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)						*4-5	
WATER REPELLENCY (HYDROPHOBIA) AATCC 79:2000 (value >300)						---	
OIL REPELLENCY (OLEOPHOBIA) EN ISO 14419:1999 – EN ISO 14419:1999/AC:2006 – AATCC 118:2002 (From 1 worst to 8 best)						---	
<div><div></div><div></div><div></div><div></div><div></div><div></div></div>							
NOTES:							
* Red & black felt-tipped pen 4 Coloured pencil 4-5 Grease 4 Orange juice 5 Synthetic soil 5 Red & blue pen 3 Crayon 4-5 Ketchup 4-5 Coffee 4-5							