



FEATURES

ARTICLE: BLEND					IN-00098-2016-B	
COMPOSITION: 53%PES 30%PP 17%CO						
WIDTH: 140 +4cm.	WEIGHT: 486	gr/m². <u>+</u> 5%	680	gr/ml. <u>+</u> 5%	WARP	WEFT
STATISTICAL NUMBER	R: 58013600 US	A :5801360020				
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)					1.7	2
ABRASION RESISTANCE (Full worm off) EN ISO 12947-2:1998					60.000	
ABRASION RESISTANCE (Change of aspect: 3000 ciclos) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)					4-5	
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)					4-5 and 4	
ASSESSMENT OF IGNITABILITY BS5852 Source 0 / EN 1021-1:2006 (cigarette test)					<u>PASS</u>	
BS5852 Source 1 / EN 1021-2:2006 (match test)						
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)					<u>5-6</u>	
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 DRY						
Degradation and loss of colour on grey scale (From 1 worst to 5 best)						
COLOUR FASTNESS TO DOMESTIC AND COMERCIAL LAUNDERING (30°) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)						
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008				<u>-2%</u>	<u>-2%</u>	
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)				<u>*4-5</u>		
WATER REPELLENCY (HYDROPHOBIA) AATCC 79:2000 (value >300)						
OIL REPELLENCY (OLEOPHOBIA) EN ISO 14419:1999 – EN ISO 14419:1999/AC:2006 – AATCC 118:2002 (From 1 worst to 8 best)						
\(\)30\(\)	X	\boxtimes	4	otin	(v	v

NOTES:

* Red & black felt-tipped pen 4-5 Coloured pencil 4-5 Grease 4 Orange juice 5 Synthetic soil 4
Red & blue pen 4 Crayon 4 Ketchup 4-5 Coffee 4-5
ATTENTION: WHEN CONFECTIONING OR WASHING THE SOFA COVER WITH VELCRO PLEASE ATTACH A PROTECTIVE

CLOTH OR STRIP OVER THE VELCRO TO AVOID DAMAGE TO THE FABRIC.