

FEATURES

ARTICLE: BOOGIE					IN-01458-2016-B-1		
COMPOSITION: 49%PES 41%PP 10%CO							
WIDTH: 140	+4cm.	WEIGHT: 496	gr/m ² . ±5%	695	gr/ml.±5%	WARP	WEFT
STATISTICAL NUMBER: 58013600 USA :5801360020							
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)					2.8		2.2
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998					35.000		
ABRASION RESISTANCE (Change of aspect: 3000 ciclos) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)					3-4		
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)					4-5		
ASSESSMENT OF IGNITABILITY BS5852 Source 0 / EN 1021-1:2006 (cigarette test)					PASS		
BS5852 Source 1 / EN 1021-2:2006 (match test)					---		
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)					5-6		
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 Degradation and loss of colour on grey scale (From 1 worst to 5 best)				DRY		---	
				WET		---	
COLOUR FASTNESS TO DOMESTIC AND COMERCIAL LAUNDERING (30°) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)					---		
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008					-3%		-2%
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)					*4-5		
WATER REPELLENCY (HYDROPHOBIA) AATCC 79:2000 (value >300)					---		
OIL REPELLENCY (OLEOPHOBIA) EN ISO 14419:1999 – EN ISO 14419:1999/AC:2006 – AATCC 118:2002 (From 1 worst to 8 best)					---		
NOTES: * Red & black felt-tipped pen 4-5 Coloured pencil 4-5 Grease 4 Orange juice 5 Synthetic soil 4 Red & blue pen 4 Crayon 4 Ketchup 4-5 Coffee 4-5 ATTENTION: WHEN CONFECTIONING OR WASHING THE SOFA COVER WITH VELCRO PLEASE ATTACH A PROTECTIVE CLOTH OR STRIP OVER THE VELCRO TO AVOID DAMAGE TO THE FABRIC.							