





FEATURES			
ARTICLE: DOLCE (IMP)		(Waterproof Laminated)	
COMPOSITION: 57%PP 38%PES 5%PU		IN-01025/2014 IN-00357/2010	
WIDTH: 140	+ 4cm.	WEIGHT: 546	gr/ml. +/- 5%
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method (180 N) Seam Slippage (mm)		1.9	2.2
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998 and EN 14465:2003/A1:2006		60.000	
ABRASION RESISTANCE (Change of aspect) EN ISO 12947/4:1998 and EN 14465:2003/A1:2006 (Annex A; 3.000 cycles) Colour Degradation on grey scale (From 1 worst to 5 best)		4-5	
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method: 2000 and 7000 cycles Pilling index (From 1 worst to 5 best)		4-5	
ASSESSMENT OF IGNITABILITY EN 1021-1:2006 // BS5852 source 0 (cigarette test)		PASSED	
EN 1021-2:2006 // BS5852 source 1 (match test)		---	
LIGHTFASTNESS TO WEATHER EN ISO 105-B04 (1000 hours) Colour degradation on blue sale (From 1 worst to 8 best)		≥6	
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002. Degradation and loss of colour on grey scale (From 1 worst to 5 best)	DRY		4-5
	WET		4-5
COLOUR FASTNESS TO DOMESTIC (30°) EN ISO 105-C06:1997/AC:2009 - Colour Degradation on grey scale (From 1 worst to 5 best)		4-5	
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000/A1:2009 – EN ISO 5077:2008		-2%	-2%
RESISTANCE TO PUTREFACTION (MOULD & BACTERIUM RESISTANCE) AATCC 30:2004		UPPER FACE	
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)		*4	
----- *Red & black marking pen 3-4 Coloured pencil 4-5 Grease 3-4 Orange juice 4-5 Synthetic soil 3-4 Red & blue ballpoint pen 3-4 Crayon 4 Ketchup 4-5 Coffee 4-5			
RESISTANCE TO WATER PENETRATION – HYDROSTATIC PRESSURE TEST EN 20811:1992		>2000mbar (20 mtrs)	
WATER FASTNESS EN ISO 105-E01:1996 Colour Degradation on grey scale (From 1 worst to 5 best)		4-5	
SWIMMING POOL CHLORINE FASTNESS EN ISO 105-E03:1993 Colour Degradation on grey scale (From 1 worst to 5 best)		4-5	
SEA WATER FASTNESS EN ISO 105-E02:1996 Colour Degradation on grey scale (From 1 worst to 5 best)		4-5	
URINE FASTNESS EN ISO 105-E02:1996 Colour Degradation on grey scale (From 1 worst to 5 best)		4-5	
<div><div></div><div></div><div></div><div></div></div>			
NOTES: ATTENTION: WHEN CONFECTIONING OR WASHING THE SOFA COVER WITH VELCRO PLEASE ATTACH A PROTECTIVE CLOTH OR STRIP OVER THE VELCRO TO AVOID DAMAGE TO THE FABRIC. Water Repellent / Repellence Protection / Waterproof In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40 ° C during at least 30 minutes. Use gentle cycle with minimal centrifugation.			

Test results in **bold** are certified by an official laboratory. Results underlined are obtained by Crevin's internal laboratory and must therefore be seen as indicative.