

ARTICLE: LIBRA					Document 11835 Document 11836 Document 11850 Hohenstein 15.8.5.0335 Hohenstein 15.8.5.0343		
COMPOSITION: 50%PP 32%PES 18%CO							
WIDTH: 140	+4cm.	WEIGHT: 440	gr/m ² ±5%	616	gr/ml±5%	WARP	WEFT
STATISTICAL NUMBER: 54078300 USA : 5407830090							
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)					1,625	1	
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998					66.000		
ABRASION RESISTANCE (Change of aspect: 3000 cycles) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)					4-5		
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)					4-5		
ASSESSMENT OF IGNITABILITY BS5852 Source 0 / EN 1021-1:2006 (cigarette test)					PASSED		
BS5852 Source 1 / EN 1021-2:2006 (match test)					Only FR(Yarn) option		
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)					≥6		
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 Degradation and loss of colour on grey scale (From 1 worst to 5 best)			DRY		4-5		
			WET		4-5		
COLOUR FASTNESS TO DOMESTIC & COMERCIAL LAUNDERING (30°) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)					---		
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008					-1%	-1%	
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)					*4-5		
HYPOALLERGENIC TEST (HOHENSTEIN LABORATORIES GmbH & Co) DIN EN ISO 10993-5:2009-10A Part5 – Non Toxic Cells					**Skin Friendly		
AW-QM-11.08.03.068. RevSta 1A – Skin Sensitization (<120%)					**72%		
NOTES: * Red & black felt-tipped pen 4-5 Coloured pencil 4-5 Grease 4 Orange juice 5 Synthetic soil 4 Red & blue pen 4 Crayon 4 Ketchup 4-5 Coffee 4-5 **Favourable fabric for allergic people ATTENTION: WHEN CONFECTIONING OR WASHING THE SOFA COVER WITH VELCRO PLEASE ATTACH A PROTECTIVE CLOTH OR STRIP OVER THE VELCRO TO AVOID DAMAGE TO THE FABRIC.							