

FEATURES

ARTICLE: MIRAGE				IN-01441/2010 805.179/07/09	
COMPOSITION: 100%PES					
WIDTH: 140	+4cm.	WEIGHT: 470 gr/m ² . <u>±</u> 5%	658 gr/ml. <u>±</u> 5%	WARP	WEFT
STATISTICAL NUMBER: 58013600 USA: 5801360020					
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)				1,9	1,8
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998				>100.000	
ABRASION RESISTANCE (Change of aspect: 3000 ciclos) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)				3-4	
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)				4-5	
ASSESSMENT OF IGNITABILITY EN 1021-1:2006 (cigarette test)				<u>PASSED</u>	
EN 1021-2:2006 (match test)				---	
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)				<u>4-5</u>	
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 Degradation and loss of colour on grey scale (From 1 worst to 5 best)			DRY	---	
			WET	---	
COLOUR FASTNESS TO DOMESTIC AMD COMERCIAL LAUNDERING (30°) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)				---	
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008				<u>-1,5%</u>	<u>-1,5%</u>
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)				<u>*4-5</u>	
WATER REPELLENCY (HYDROPHOBIA) AATCC 79:2000 (value >300)				---	
OIL REPELLENCY (OLEOPHOBIA) EN ISO 14419:1999 – EN ISO 14419:1999/AC:2006 – AATCC 118:2002 (From 1 worst to 8 best)				---	
NOTES: * Red & black felt-tipped pen 4 Coloured pencil 4-5 Grease 4 Orange juice 5 Synthetic soil 5 Red & blue pen 4 Crayon 4-5 Ketchup 4-5 Coffee 4-5					