

FEATURES

ARTICLE: OPTIM					IN-00647-2016-B Document 013029		
FACE FABRIC COMPOSITION : 50%LI 50%PES TOTAL COMPOSITION : 56%PES 36%LI 8%CO							
WIDTH: 140	+4cm.	WEIGHT: 571	gr/m ² . ±5%	800	gr/ml.±5%	WARP	WEFT
ESTADISTIC NUMBER: 58013600 USA : 5801360020							
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)						2.9	3
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998						58.000	
ABRASION RESISTANCE (Change of aspect: 3000 ciclos) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)						4	
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)						4	
ASSESSMENT OF IGNITABILITY EN 1021-1:2006 (cigarette test)						PASSED	
EN 1021-2:2006 (match test)						---	
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)						6	
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 Degradation and loss of colour on grey scale (From 1 worst to 5 best)				DRY		---	
				WET		---	
COLOUR FASTNESS TO DOMESTIC AND COMERCIAL LAUNDERING (30º) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)						---	
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008						-2%	-3%
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)						---	
WATER REPELLENCY (HYDROPHOBIA) Spray Test AATCC22 (From 0 worst to 100 best)						---	
OIL REPELLENCY (OLEOPHOBIA) AATCC 118:2002 (From 1 worst to 8 best)						---	
<div><div></div><div></div><div></div><div></div><div></div></div>							
NOTES: ATTENTION: WHEN CONFECTIONING OR WASHING THE SOFA COVER WITH VELCRO PLEASE ATTACH A PROTECTIVE CLOTH OR STRIP OVER THE VELCRO TO AVOID DAMAGE TO THE FABRIC. Linen is a material whose fibres tend to shred. This effect is part of the fabric's nature Slight colour variations may occur from batch to batch							