





ARTICLE: PIXEL					IN-01925/2011		
COMPOSITION: 73%PP 27%PES							
WIDTH: 140	+4cm.	WEIGHT: 570	gr/m <sup>2</sup> . ±5%	798	gr/ml.±5%	WARP	WEFT
ESTADISTIC NUMBER: 54077300 USA : 5407732060							
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)						3.5	3.5
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998						26.000	
ABRASION RESISTANCE (Change of aspect: 3000 ciclos) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)						3	
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)						4-5	
ASSESSMENT OF IGNITABILITY EN 1021-1:2006 (cigarette test)						PASSED	
EN 1021-2:2006 (match test)						---	
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)						≥6	
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 Degradation and loss of colour on grey scale (From 1 worst to 5 best)				DRY		4-5	
				WET		4-5	
COLOUR FASTNESS TO DOMESTIC AMD COMERCIAL LAUNDERING (30°) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)						---	
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008						-1,5%	-1%
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)						*4-5	
WATER REPELLENCY (HYDROPHOBIA) AATCC 79:2000 (value >300)						---	
OIL REPELLENCY (OLEOPHOBIA) EN ISO 14419:1999 – EN ISO 14419:1999/AC:2006 – AATCC 118:2002 (From 1 worst to 8 best)						---	
<div><div></div><div></div><div></div><div></div></div>							
NOTES: RAPPORT 2,9CM X 1,6CM ±3,5% * Red & black felt-tipped pen 4-5 Coloured pencil 4-5 Grease 4 Orange juice 5 Synthetic soil 4 Red & blue pen 4 Crayon 4 Ketchup 4-5 Coffee 4-5 ATTENTION: WHEN CONFECTIONING OR WASHING THE SOFA COVER WITH VELCRO PLEASE ATTACH A PROTECTIVE CLOTH OR STRIP OVER THE VELCRO TO AVOID DAMAGE TO THE FABRIC. PLEASE PAY ATTENTION TO THE FABRIC'S ELASTICITY WHEN CONFECTIONING THE SOFA							