

**Client:** Crevin, s.a.  
Pol.Ind.Santa Margarita I  
C/Llobregat, 21  
08223 Terrassa (BCN)  
Spain

**Entry No:** 64127-01

**Date received:** 04/03/2014

**Client's Description:** Sample of fabric Tonic

### TEST REPORT

**Test Required:** Flammability in accordance with The Furniture and Furnishings (Fire) (Safety) Regulations 1988 and Amendments Schedule 4 Part I and Schedule 5 Part I

**Pre-treatment:** None

**Conditioning:** A minimum of 96 hours at 50 +/- 20% Relative Humidity, 20 +/- 5°C

**Method of Test:** BS 5852 : Part 1 : 1979

**Date of Test:** 13/03/2014

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
0 (cigarette)	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
1 (butane flame)	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

**Note:** 20-22 kg/m<sup>3</sup> non fire retardant polyurethane foam was used as the filling.

### Comments

On the basis of the tests carried out this sample of fabric meets the requirements of Schedule 4 Part I and Schedule 5 Part I.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



D Brockbank  
Senior Technologist  
14<sup>th</sup> March 2014

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



**Client:** Crevin, s.a.  
Pol.Ind.Santa Margarita I  
C/Llobregat, 21  
08223 Terrassa (BCN)  
Spain

**Entry No:** 68662

**Date received:** 29/01/2015

**Client's Description:** Sample of fabric: Tonic

### TEST REPORT

**Test Required:** Flammability BS 7176 Low Hazard  
**Pre-treatment:** None  
**Conditioning:** A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2° C  
**Method of Test:** BS EN 1021-1: 2006 – smouldering cigarette  
BS EN 1021-2: 2006 – match flame equivalent  
**Date of Test:** 13/02/2015

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	No flaming or progressive smouldering was observed after removal of the butane flame.	PASS

**Note:** A 35 kg/m<sup>3</sup> CMHR foam (Carpenters RX36-125) which meets the requirements of Annex A of BS 7176 was used as the filling


The above results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

#### Comments

BS 7176 : 2007 + A1 : 2011 relates to labelling of furniture. If an item of furniture was manufactured from a composite of the fabric and foam tested above then it would comply with the low hazard category flammability requirements provided that it was tested every 2.500 units or once per month as required by Para 5 of BS 7176.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



D. Brockbank.  
Materials Testing Manager  
16<sup>th</sup> February 2015



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



**Client:** Crevin, s.a.  
Pol.Ind.Santa Margarita I  
C/Llobregat, 21  
08223 Terrassa (BCN)  
Spain

**Entry No:** 64127

**Date received:** 04/03/2014

**Client's Description:** Sample of fabric Tonic

### TEST REPORT

**Test Required:** Flammability

**Pre-treatment:** None

**Conditioning:** A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C

**Method of Test:** BS EN 1021-1:2006 – smouldering cigarette  
BS EN 1021-2:2006 – match flame equivalent

**Date of Test:** 13/03/2014

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

**Note:** 20-22 kg/m<sup>3</sup> non fire retardant polyurethane foam was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



D Brockbank  
Senior Technologist  
14<sup>th</sup> March 2014

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

