

	Doc. nr. : SK-71	
	Page : 1 of 1	
	Revision nr. : 5	
	Approved by : BV	
Test report Textile Pilling NS-EN ISO 12945-2 :2000		

Client Crevin,s.a. Pol. Ind. Santa Margarita I C/ Llobregat, 21 08223 TERRASSA Spania		Product T-93468	
		Product specification - tested object	
Client's reference Pep Margarit		R-no. R15686	
Date 18.02.2016	Date of receipt, tested object 15.02.2016	Test completed date 16.02.2016	Rev. no. / Rev. date 0/

Manufacturer:

Composition:

Loading Mass : 415 g

Type felt: Woven

The samples are conditioned at 20 degrees C and 65 % relative humidity for 18 hours

Numerical assessment of pilling is done on a Martindale abrasion tester according to NS-EN ISO 12945-2. The samples are given a multi-directional movement and are rubbed against fabric of 100% wool (SM 25). 3 samples are used and they are examined on 500, 1000, 2000 and 5000 rubs. The average on each stage is reported as the pilling grade.

The samples are examined on a scale from 1-5 where 5 is best. Examined by 1 person.

Results: 2000 Cycles: 4-5 7000 Cycles: 4-5

Comments:
Deviations from test standards:



Bård Vestre
Manager