

	Doc. nr. : SK-71	
	Page : 1 of 1	
	Revision nr. : 5	
	Approved by : BV	
<b>Test report Textile Pilling</b> <b>NS-EN ISO 12945-2 :2000</b>		

Client <b>Crevin,s.a.</b> <b>Pol.Ind.Sta. Margarita</b> <b>c/ Llobregat,</b>  <b>21 08223 Terassa (Barcelona)</b> <b>Spania</b>		Product <b>URUS-FR</b>  Product specification - tested object	
Client's reference <b>Pep Margarit</b>		R-no. <b>R15385</b>	
Date 19.02.2015	Date of receipt, tested object 16.02.2015	Test completed date 19.02.2015	Rev. no. / Rev. date 0/

Manufacturer:

Composition:

Loading Mass : 415 g

Type felt: Woven

The samples are conditioned at 20 degrees C and 65 % relative humidity for 18 hours

Numerical assessment of pilling is done on a Martindale abrasion tester according to NS-EN ISO 12945-2. The samples are given a multi-directional movement and are rubbed against fabric of 100% wool (SM 25). 3 samples are used and they are examined on 500, 1000, 2000 and 5000 rubs. The average on each stage is reported as the pilling grade.

The samples are examined on a scale from 1-5 where 5 is best. Examined by 1 person.

<b>Results:</b> <b>2000 Cycles:5</b> <b>7000 Cycles:5</b>
---

<b>Comments:</b>
<b>Deviations from test standards: Intervals 2000,7000</b>



Bård Vestre  
Manager