

Client: Crevin, s.a.
Pol.Ind.Santa Margarita I
C/Llobregat, 21
08223 Terrassa (BCN)
Spain

Entry No: 65611

Date received: 16/06/2014

Client's Description: Sample of fabric Divine-FR

TEST REPORT

Test Required: Flammability in accordance with The Furniture and Furnishings (Fire) (Safety) Regulations 1988 and Amendments Schedule 4 Part I and Schedule 5 Part I

Pre-treatment: None

Conditioning: A minimum of 96 hours at 50 +/- 20% Relative Humidity, 20 +/- 5°C

Method of Test: BS 5852 : Part 1 : 1979

Date of Test: 24/06/2014

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
0 (cigarette)	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
1 (butane flame)	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

Note: 20-22 kg/m³ non fire retardant polyurethane foam was used as the filling.

Comments

On the basis of the tests carried out this sample of fabric meets the requirements of Schedule 4 Part 1 and Schedule 5 Part I.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.




Geoff Briggs C.Text., A.T.I.
Head of laboratory
25th June 2014

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



Client: Crevin, s.a.
Pol.Ind.Santa Margarita I
C/Llobregat, 21
08223 Terrassa (BCN)
Spain

Entry No: 65611-02

Date received: 16/06/2014

Client's Description: Sample of fabric Divine-FR

TEST REPORT

Test Required: Flammability BS 7176 Low Hazard

Pre-treatment: None

Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C

Method of Test: BS EN 1021-1:2006 – smouldering cigarette
BS EN 1021-2:2006 – match flame equivalent

Date of Test: 24/06/2014

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

Note: A 35 kg/m³ CMHR foam (Carpenters RX36-125) which meets the requirements of Annex A of BS 7176 was used as the filling


The above results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comments

BS 7176 : 2007 + A1 : 2011 relates to labelling of furniture. If an item of furniture was manufactured from a composite of the fabric and foam tested above then it would comply with the low hazard category flammability requirements provided that it was tested every 2.500 units or once per month as required by Para 5 of BS 7176.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.




D J Brockbank
Materials Testing Manager
26th January 2015

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



Client: Crevin, s.a.
Pol.Ind.Santa Margarita I
C/Llobregat, 21
08223 Terrassa (BCN)
Spain

Entry No: 65611-01

Date received: 16/06/2014

Client's Description: Sample of fabric Divine-FR

TEST REPORT

Test Required: Flammability
Pre-treatment: None
Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C
Method of Test: BS EN 1021-1:2006 – smouldering cigarette
BS EN 1021-2:2006 – match flame equivalent
Date of Test: 24/06/2014

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

Note: A 35 kg/m³ CM foam (Carpenters RX36-125) was used as the filling.


The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



Geoff Briggs C.Text., A.T.I.
Head of laboratory
25th June 2014



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



INFORME DE ENSAYO / TEST REPORT

N° **2015AN1021**

FECHA RECEPCIÓN
DATE OF RECEPTION

13/05/2015

SOLICITANTE / APPLICANT

CREACIONES DE VELOURS INDUSTRIALES,
SA(CREVIN)
C/ LLOBREGAT, 21
ES-08223 Terrassa
Barcelona

Att. PEP MARGARIT

FECHA ENSAYOS
DATE TEST

Inicio / Starting: 15/05/2015
Finalización / Ending: 18/05/2015

DESCRIPCIÓN
E IDENTIFICACIÓN
DE LAS MUESTRAS

MUESTRAS REFERENCIADAS / SAMPLES REFERENCED:

- "TEJIDO DIVINE 2 DM265/01".

DESCRIPTION AND
IDENTIFICATION OF
SAMPLES

ENSAYOS
REALIZADOS
TESTS CARRIED OUT

- CLASIFICACIÓN DE CIGARRILLO ENCENDIDO POR LA RESISTENCIA DE LOS COMPONENTES DE MUEBLES TAPIZADOS / TEST AND CLASSIFICATION SYSTEM FOR CIGARETTE IGNITION RESISTANCE OF COMPONENTS OF UPHOLSTERED FURNITURE

ENAC es firmante del Acuerdo Multilateral (MLA), (Acuerdo de Reconocimiento Mutuo MRA) de la European Cooperation for Accreditation (EA) y de la International Laboratory Accreditation Cooperation (ILAC), en materia de ensayos. / ENAC is a signatory to the Multilateral Agreement (MLA), (MRA Mutual Recognition Agreement) of the European Cooperation for Accreditation (EA) and the International Laboratory Accreditation Cooperation (ILAC), in testing.

SE ADJUNTAN
ATTACHED

MUESTRA(S)
SAMPLE(S)

LACRADA(S)
SEALED

PÁG.
PAGE

1

DE
OF

5