

DIVINE-FR

data sheet

Design	DIVINE-FR		
Composition	46%PP 41%PES 7%MA 6%CO		
Width	140		
Linear Weight	756 gr/lm ± 5%		
Seam slippage resistance EN ISO 13936/2	WARP	2,9	
	WEFT	2	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	56.000 (B)	
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5	
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	5		
Assessment of ignitability	Cigarette test / Match test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CAL TB117:sect I 2013 NFPA 260:2013	PASS	
Lightfastness EN ISO 105-B02	6-7		
Colour fastness to rubbing EN ISO 105-X12.	DRY	5	
	WET	5	
Dimensional change in domestic washing and drying EN ISO 3759 / EN ISO 6330 / EN ISO 5077	WARP	-2%	
	WEFT	-1,5%	
Cleaning	   		
Environment	• Oeko-Tex Certified Yarn • 100% free of heavy metals and halogens • ISO 14001 certified • Resource-efficient manufacturing		

