

LOGGIA (IMP)

data sheet

Design	LOGGIA (IMP)	
Composition	57%PP 38%PES 5%PU	
Width	140	
Linear Weight	546 gr/lm $\pm$ 5%	
Seam slippage resistance EN ISO 13936/2	WARP	1,9
	WEFT	2,2
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	60.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Assessment of ignitability	Cigarette test BS5852 EN 1021-1	PASS
Colour fastness to rubbing EN ISO 105-X12	DRY	4-5
	WET	4-5
Lightfastness to weather EN ISO 105-B04 (1000 hours)	>6	
Dimensional change in domestic washing and drying EN ISO 3759 · EN ISO 6330 · EN ISO 5077	WARP	-2%
	WEFT	-2%
Colour fastness to domestic (30°) EN ISO 105-C06	4-5	
Resistance to water penetration - hydrostatic pressure test EN 20811	>2000mbar	
Water fastness EN ISO 105-E01	4-5	
Swimming pool chlorine fastness EN ISO 105-E03	4-5	
Sea water fastness EN ISO 105-E02	4-5	
Urine fastness EN ISO 105-E01	4-5	
Cleaning	   	