

URUS

data sheet

Design	URUS	
Composition	50%PP 31%PES 19%CO	
Width	140	
Linear Weight	658 gr/lm $\pm$ 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	32.500 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	3-4
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Lightfastness EN ISO 105-B02	>6	
Cleaning	   	

Efficiency[®]