

CLUB-FR

data sheet

Design	CLUB-FR	
Composition	69%PES 17%MA 14%CO	
Width	140	
Linear Weight	700 gr/lm $\pm$ 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	30.000 (B)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Lightfastness EN ISO 105-B02	6	
Cleaning	   	