

OPTIM-FR

data sheet

Design	OPTIM-FR	
Face fabric composition	50%LI 50%PES	
Composition	44%PES 34%LI 12%MA 10%CO	
Width	140	
Linear Weight	870 gr/lm $\pm$ 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	58.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4	
Lightfastness EN ISO 105-B02	6	
Cleaning	    	