

Nepshaw Lane South, Morley, Leeds, LS27 7JQ Materials Testing Manager: D. J. Brockbank

t: 0113 393 9791

e: dale.brockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



OTEST REPORT

Client: Crevin, s.a.

Pol.Ind.Santa Margarita I

C/Llobregat, 21

08223 Terrassa (BCN)

Spain

Entry No: 101094

Date received: 27/07/2018

Client's Description: Sample of fabric: VELVETY-FR, composition: 86% PES 9% CO 5% MA

Test Required: Flammability BS 7176 Low Hazard

Pre-treatment: None

Conditioning: A minimum of 24 hours at 50+/-5% Relative Humidity, 23+/-2°C

Date Tests Completed: 08/08/2018

Method of Test: BS EN 1021-1: 2006 – smouldering cigarette

BS EN 1021-2: 2006 - match flame equivalent

Ignition Source	Observations	Result
Smouldering	No flaming or progressive smouldering was observed within one hour of	PASS
cigarette	placement of the cigarettes.	
Match flame	Flaming ceased within the specified two minute period after removal of the	PASS
equivalent	butane flame and no progressive smouldering occurred.	

Note: A 35 kg/m³ CMHR foam (Carpenters RX36-125) which meets the requirements of Annex A of BS 7176

was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comments

BS 7176: 2007 + A1: 2011 relates to labelling of furniture. If an item of furniture was manufactured from a composite of the fabric and foam tested above then it would comply with the low hazard category flammability requirements provided that it was tested every 2.500 units or once per month as required by Para 5 of BS 7176.

-----End of Document------

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank Materials Testing Manager 09 August 2018

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.









Nepshaw Lane South, Morley, Leeds, LS27 7JQ Materials Testing Manager: D. J. Brockbank

t: 0113 393 9791

e: dale.brockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



TEST REPORT

Client: Crevin, s.a.

Pol.Ind.Santa Margarita I

C/Llobregat, 21

08223 Terrassa (BCN)

Spain

Entry No: 101094-01

Date received: 27/07/2018

Client's Description: Sample of fabric: VELVETY-FR, composition: 86% PES 9% CO 5% MA

Test Required: Flammability

Pre-treatment: None

Conditioning: A minimum of 24 hours at 50+/-5% Relative Humidity, 23+/-2°C

Date Tests Completed: 08/08/2018

Method of Test: BS EN 1021-1:2014 – smouldering cigarette

BS EN 1021-2:2014 - match flame equivalent

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
Smouldering	No flaming or progressive smouldering was observed within one hour of	PASS
cigarette	placement of the cigarettes.	
Match flame	Flaming ceased within the specified two minute period after removal of the	PASS
equivalent	butane flame and no progressive smouldering occurred.	

Note: A 35 kg/m³ CMHR foam (Carpenters RX36-125) was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

------End of Document------

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank
Materials Testing Manager
09 August 2018

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

Tests marked F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.

Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.







Nepshaw Lane South, Morley, Leeds, LS₂₇7JQ Materials Testing Manager: D. J. Brockbank

t: 0113 393 9791

e: dale.brockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



TEST REPORT

Client: Crevin, s.a.

Pol.Ind.Santa Margarita I

C/Llobregat, 21

08223 Terrassa (BCN)

Spain

Entry No: 101094-02 **Date received:** 27/07/2018

Client's Description: Sample of fabric: VELVETY-FR, composition: 86% PES 9% CO 5% MA

Test Required: Flammability in accordance with The Furniture and Furnishings (Fire) (Safety)

Regulations 1988 and Amendments Schedule 4 Part I and Schedule 5 Part I

Pre-treatment: None

Conditioning: A minimum of 96 hours at 50+/-20% Relative Humidity, 20+/-5°C

Date Tests Completed: 03/08/2018

Method of Test: BS 5852: Part 1: 1979

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
0 (cigarette)	No flaming or progressive smouldering was observed within one hour of	PASS
	placement of the cigarettes.	
1 (butane flame)	Flaming ceased within the specified two minute period after removal of the	PASS
	butane flame and no progressive smouldering occurred.	

Note: A 20-22 kg/m3 non fire retardant polyurethane foam was used as the filling for the cigarette tests.

Comments

On the basis of the tests carried out this sample of fabric meets the requirements of Schedule 4 Part I and also meets Schedule 5 Part I.

-----End of Document------

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank

Materials Testing Manager

03 August 2018

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.





