

BORA-BORA

data sheet

Design	BORA-BORA	
Composition	82%PP 18%PES	
Width	140	
Linear Weight	1050 gr/lm $\pm$ 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	>100.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	5	
Lightfastness EN ISO 105-B02	>6	
Cleaning		