

BORA-BORA (IMP)

data sheet

Design	BORA-BORA (IMP)	
Composition	80%PP 18%PES 2%PU	
Width	140	
Linear Weight	1070 gr/lm ± 5%	
Seam slippage resistance <small>EN ISO 13936/2</small>	WARP	2
	WEFT	3
Abrasion Resistance	End Point (A) / Fully worn off (B) <small>EN ISO 12947-2</small>	>100.000 (A)
	Change aspect 3000c <small>EN ISO 12947/2 / EN 14465 / EN ISO 105-A02</small>	-
Pilling resistance (2000 and 5000 cycles) <small>EN ISO 12945/2</small>	5	
Assessment of ignitability	Cigarette test / Match test <small>BS5852 0/1 EN 1021 1/2 IMO MSC(67) RESOLUTION A.652 (16)</small>	PASS
Colour fastness to rubbing <small>EN ISO 105-X12</small>	DRY	4-5
	WET	4-5
Lightfastness to weather <small>EN ISO 105-B04 (1000 hours)</small>	>6	
Dimensional change in domestic washing and drying <small>EN ISO 3759 · EN ISO 6330 · EN ISO 5077</small>	WARP	-3%
	WEFT	-1%
Colour fastness to domestic (30°) <small>EN ISO 105-C06</small>	4-5	
Resistance to water penetration - hydrostatic pressure test <small>EN 20811</small>	>2000mbar	
Water fastness <small>EN ISO 105-E01</small>	4-5	
Swimming pool chlorine fastness <small>EN ISO 105-E03</small>	4-5	
Sea water fastness <small>EN ISO 105-E02</small>	4-5	
Urine fastness <small>EN ISO 105-E01</small>	4-5	
Cleaning		