





DAS-FR

data sheet

| | | |
|---|---|------------|
| Design | DAS-FR | |
| Composition | 49%PP 21%MA 16%CO 14%PES | |
| Width | 140 | |
| Linear Weight | 623 gr/lm \pm 5% | |
| Seam slippage resistance <small>EN ISO 13936/2</small> | WARP | 3 |
| | WEFT | 3 |
| Abrasion Resistance | End Point (A) / Fully worn off (B) <small>EN ISO 12947-2</small> | 32.000 (A) |
| | Change aspect 3000c <small>EN ISO 12947/2 / EN 14465 / EN ISO 105-A02</small> | 5 |
| Pilling resistance (2000 and 5000 cycles) <small>EN ISO 12945/2</small> | 5 | |
| Assessment of ignitability | Cigarette test / Match test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CALTB117:sect I 2013 NFPA 260:2013 | PASS |
| Lightfastness <small>EN ISO 105-B02</small> | >6 | |
| Colour fastness to rubbing <small>EN ISO 105-X12</small> | DRY | 5 |
| | WET | 5 |
| Dimensional change in domestic washing and drying <small>EN ISO 3759 / EN ISO 6330 / EN ISO 5077</small> | WARP | -1,5% |
| | WEFT | -1,5% |
| Cleaning |     | |
| Environment | <ul style="list-style-type: none"> • Oeko-Tex Certified Yarn • 100% free of heavy metals and halogens • ISO 14001 certified • Resource-efficient manufacturing | |

efficiency

