

GEMINI-FR

data sheet

Design	GEMINI-FR	
Composition	39%PES 38%PP 13%MA 10%CO	
Width	140	
Linear Weight	680 gr/lm \pm 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	26.000 (B)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Lightfastness EN ISO 105-B02	5-6	
Cleaning	   	