

ORIGAMI

data sheet

Design	ORIGAMI	
Composition	40%PES 32%PP 17%CV 7%LI 4%CO	
Width	140	
Linear Weight	950 gr/lm \pm 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	25.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4	
Lightfastness EN ISO 105-B02	5-6	
Cleaning		