





# SUBLIM-FR

data sheet

Design	SUBLIM-FR	
Composition	78%PES 12%MA 10%CO	
Width	140	
Linear Weight	605 gr/lm $\pm$ 5%	
Seam slippage resistance EN ISO 13936/2	WARP	2,9
	WEFT	3
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	80.000 (B)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	5	
Assessment of ignitability	Cigarette test / Match test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CALTB117:sect I 2013 NFPA 260:2013	PASS
Lightfastness EN ISO 105-B02	5-6	
Colour fastness to rubbing EN ISO 105-X12.	DRY	4-5
	WET	4-5
Dimensional change in domestic washing and drying EN ISO 3759 / EN ISO 6330 / EN ISO 5077	WARP	-2%
	WEFT	-3%
Cleaning	   	
Environment	<ul style="list-style-type: none"> <li>• Oeko-Tex Certified Yarn</li> <li>• 100% free of heavy metals and halogens</li> <li>• ISO 14001 certified</li> <li>• Resource-efficient manufacturing</li> </ul>	

efficiency

