


TONIC

data sheet

Design	TONIC	
Face fabric composition	60%WO 40%PP	
Composition	34%WO 28%PES 23%PP 15%CO	
Width	140	
Linear Weight	750 gr/lm \pm 5%	
Seam slippage resistance EN ISO 13936/2	WARP	2,1
	WEFT	2,1
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	56.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	5 and 4-5	
Assessment of ignitability	Cigarette test / Match test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CALTB1 17:sect 1 2013 NFPA 260:2013	PASS
Lightfastness EN ISO 105-B02	5-6	
Colour fastness to rubbing EN ISO 105-X12.	DRY	4-5
	WET	4
Dimensional change in domestic washing and drying EN ISO 3759 / EN ISO 6330 / EN ISO 5077	WARP	-3%
	WEFT	-3%
Cleaning		
Environment	<ul style="list-style-type: none"> • Oeko-Tex Certified Yarn • 100% free of heavy metals and halogens • ISO 14001 certified • Resource-efficient manufacturing 	

twoworlds

