

VITA (IMP)

data sheet

Design	VITA (IMP)	
Composition	57%PP 38%PES 5%PU	
Width	140	
Linear Weight	546 gr/lm ± 5%	
Seam slippage resistance <small>EN ISO 13936/2</small>	WARP	1,9
	WEFT	2,2
Abrasion Resistance	End Point (A) / Fully worn off (B) <small>EN ISO 12947-2</small>	60.000 (A)
	Change aspect 3000c <small>EN ISO 12947/2 / EN 14465 / EN ISO 105-A02</small>	4-5
Pilling resistance (2000 and 5000 cycles) <small>EN ISO 12945/2</small>	4-5	
Assessment of ignitability	Cigarette test <small>BS5852 EN 1021-1</small>	PASS
Colour fastness to rubbing <small>EN ISO 105-X12</small>	DRY	4-5
	WET	4-5
Lightfastness to weather <small>EN ISO 105-B04 (1000 hours)</small>	>6	
Dimensional change in domestic washing and drying <small>EN ISO 3759 · EN ISO 6330 · EN ISO 5077</small>	WARP	-2%
	WEFT	-2%
Colour fastness to domestic (30°) <small>EN ISO 105-C06/AC</small>	4-5	
Resistance to water penetration - hydrostatic pressure test <small>EN 20811</small>	>2000mbar	
Water fastness <small>EN ISO 105-E01</small>	4-5	
Swimming pool chlorine fastness <small>EN ISO 105-E03</small>	4-5	
Sea water fastness <small>EN ISO 105-E02</small>	4-5	
Urine fastness <small>EN ISO 105-E01</small>	4-5	
Cleaning	   	