


# DAS

data sheet

Design		DAS
Composition		50%PP 31%PES 19%CO
Width		140
Linear Weight		659 gr/lm $\pm$ 5%
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	36.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	3-4
Assessment of ignitability	Cigarette test BS5852 0 EN 1021 1 CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2		4-5
Lightfastness EN ISO 105-B02		>6
Cleaning		

## efficiency

