

# GALAXY

data sheet

Design	GALAXY	
Composition	58%WO 19%PP 17%PES 6%CO	
Width	138	
Linear Weight	835 gr/lm $\pm$ 5%	
Seam slippage resistance <small>EN ISO 13936/2</small>	WARP	2
	WEFT	2
Abrasion Resistance	End Point (A) / Fully worn off (B) <small>EN ISO 12947-2</small>	35.000 (A)
	Change aspect 3000c <small>EN ISO 12947/2 / EN 14465 / EN ISO 105-A02</small>	4
Pilling resistance (2000 and 5000 cycles) <small>EN ISO 12945/2</small>	5	
Assessment of ignitability	Cigarette test / Match test <small>BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CALTB117:sect 1 2013 NFPA 260:2013</small>	PASS
Lightfastness <small>EN ISO 105-B02</small>	5-6	
Colour fastness to rubbing <small>EN ISO 105-X12</small>	DRY	4-5
	WET	4
Dimensional change in domestic washing and drying <small>EN ISO 3759 / EN ISO 6330 / EN ISO 5077</small>	WARP	3%
	WEFT	3%
Cleaning		
Environment	<ul style="list-style-type: none"> <li>• Oeko-Tex Certified Yarn</li> <li>• 100% free of heavy metals and halogens</li> <li>• ISO 14001 certified</li> <li>• Resource-efficient manufacturing</li> </ul>	

wool

