


SACCO

data sheet

Design	SACCO	
Composition	80%PP 15%PES 5%CO	
Width	140	
Weight	800 gr/lm $\pm$ 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2:1998	80.000 (A)
	Change aspect 3000 cycles EN ISO 12947/4:1998 - EN 14465:2003	4-5
Assessment of ignitability	Cigarette test BS5852 0 EN 1021 1 CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Pilling resistance EN ISO 12945/2:2000	4-5	
Lightfastness EN ISO 105-B02:1998 EN ISO105-B02/A01:2002	>6	
Washing conditions		

efficiency

