


# ONIX

data sheet

Design		ONIX
Composition		68%PES 24%PP 8%CO
Width		140
Weight		620 gr/lm $\pm$ 5%
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2:1998	70.000 (A)
	Change aspect 3000 cycles EN ISO 12947/4:1998 - EN 14465:2003	4-5
Assessment of ignitability	Cigarette test BS5852 0 EN 1021 1 CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Pilling resistance		4-5 EN ISO 12945/2:2000
Lightfastness		>6 EN ISO 105-B02:1998 EN ISO105-B02/A01:2002
Washing conditions		

## efficiency

