

ITO

data sheet

Design	ITO	
Composition	71%PES 20%PP 9%CO	
Width	140	
Weight	812 gr/lm \pm 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2:1998	>100.000 (A)
	Change aspect 3000 cycles EN ISO 12947/4:1998 - EN 14465:2003	4-5
Assessment of ignitability	Cigarette test BS5852 0 EN 1021 1 CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Pilling resistance	EN ISO 12945/2:2000	4-5
Lightfastness	EN ISO 105-B02:1998 EN ISO105-B02/A01:2002	5-6
Washing conditions		

efficiency

