

TONIC

data sheet

Design	TONIC		
Face fabric composition	60%WO 40%PP		
Composition	34%WO 28%PES 23%PP 15%CO		
Width	140		
Linear Weight	750 gr/lm ± 5%		
Seam slippage resistance EN ISO 13936/2	WARP	2,1	
	WEFT	2,1	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	56.000 (A)	
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5	
Assessment of ignitability	Cigarette test / Match test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CAL TB117:sect 1 2013 NFPA 260:2013	PASS	
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5		
Lightfastness EN ISO 105-B02	7-8		
Colour fastness to rubbing EN ISO 105-X12.	DRY	4-5	
	WET	4	
Dimensional change in domestic washing and drying EN ISO 3759 / EN ISO 6330 / EN ISO 5077	WARP	-3%	
	WEFT	-3%	
Cleaning	    		
Environment	• Oeko-Tex Certified Yarn • 100% free of heavy metals and halogens • crevin, s.a.: ISO 14001 certified • Resource-efficient manufacturing		

wool

