





DIVINE-FR

data sheet

Design	DIVINE-FR	
Composition	46%PP 41%PES 7%MA 6%CO	
Width	140	
Linear Weight	756 gr/lm \pm 5%	
Seam slippage resistance <small>EN ISO 13936/2</small>	WARP	2,9
	WEFT	2
Abrasion Resistance	End Point (A) / Fully worn off (B) <small>EN ISO 12947-2</small>	56.000 (B)
	Change aspect 3000c <small>EN ISO 12947/2 / EN 14465 / EN ISO 105-A02</small>	4-5
Assessment of ignitability	Cigarette test / Match test <small>BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CALTBI 17:sect 1 2013 NFPA 260.2013</small>	PASS
Pilling resistance (2000 and 5000 cycles) <small>EN ISO 12945/2</small>	5	
Lightfastness <small>EN ISO 105-B02</small>	6-7	
Colour fastness to rubbing <small>EN ISO 105-X12</small>	DRY	5
	WET	5
Dimensional change in domestic washing and drying <small>EN ISO 3759 / EN ISO 6330 / EN ISO 5077</small>	WARP	-2%
	WEFT	-1,5%
Cleaning	   	
Environment	<ul style="list-style-type: none"> • Oeko-Tex Certified Yarn • 100% free of heavy metals and halogens • crevin, s.a.: ISO 14001 certified • Resource-efficient manufacturing 	

efficiency

