

DROM-FR

data sheet

Design		DROM-FR	
Composition		47%PES 23%PP 17%MA 13%CO	
Width		140	
Linear Weight		670 gr/lm ± 5%	
Seam slippage resistance EN ISO 13936/2		WARP	3,8
		WEFT	3,9
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	50.000 (B)	
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5	
Assessment of ignitability	Cigarette test / Match test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CAL TB117:sect 1 2013 NFPA 260:2013	PASS	
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2		4-5	
Lightfastness EN ISO 105-B02		6-7	
Colour fastness to rubbing EN ISO 105-X12.	DRY	4-5	
	WET	4-5	
Dimensional change in domestic washing and drying EN ISO 3759 / EN ISO 6330 / EN ISO 5077		WARP	-2%
		WEFT	-1,5%
Cleaning		   	
Environment		• Oeko-Tex Certified Yarn • 100% free of heavy metals and halogens • crevin, s.a.: ISO 14001 certified • Resource-efficient manufacturing	

efficiency

