

SONNET-FR

data sheet

Design	SONNET-FR	
Composition	59%PP 15%MA 14%PES 12%CO	
Width	140	
Linear Weight	620 gr/lm \pm 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	44.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	4-5
Assessment of ignitability	Cigarette test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Lightfastness EN ISO 105-B02	>6	
Cleaning		

efficiency

