

TWIN-FR

data sheet

Design	TWIN-FR	
Composition	76%PP 10%PES 8%MA 6%CO	
Width	140	
Linear Weight	795 gr/lm ± 5%	
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	35.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	3-4
Assessment of ignitability	Cigarette test BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Lightfastness EN ISO 105-B02	>6	
Cleaning		

efficiency

