

FIJI (IMP)

data sheet

Design	FIJI (IMP)	
Composition	81%PP 15%PES 4%PU	
Width	140	
Linear Weight	784 gr/lm ± 5%	
Seam slippage resistance EN ISO 13936/2	WARP	2
	WEFT	2,6
Abrasion Resistance	End Point (A) / Fully worn off (B) EN ISO 12947-2	30.000 (A)
	Change aspect 3000c EN ISO 12947/2 / EN 14465 / EN ISO 105-A02	-
Pilling resistance (2000 and 5000 cycles) EN ISO 12945/2	4-5	
Assessment of ignitability	(Cigarette / Match) BS5852 0/1 EN 1021 1/2 BS7176 Low hazard CAL TB117:sect 1 2013 NFPA 260:2013	PASS
Colour fastness to rubbing EN ISO 105-X12	DRY	4-5
	WET	4-5
Lightfastness to weather EN ISO 105-B04 (1000 hours)	>6	
Dimensional change in domestic washing and drying EN ISO 3759 · EN ISO 6330 · EN ISO 5077	WARP	-2%
	WEFT	-0,8%
Colour fastness to domestic (30°) EN ISO 105-C06/AC	4-5	
Resistance to water penetration - hydrostatic pressure test EN 20811	>2000mbar	
Swimming pool chlorine fastness EN ISO 105-E03	4-5	
Sea water fastness EN ISO 105-E02	4-5	
Urine fastness EN ISO 105-E01	4-5	
Cleaning		