






Characteristics 	Specifications 	Care 	Ignitability 	Environment 
Total composition 36%PES 30%PP 19%MA 15%CO  Width 140 + 4cm Weight 486 gr/m² ± 5 % 680 gr/lm ± 5 % Custom code UE: 5801.36.00 USA: 5801.36.00.20 Laboratory test number IN-00098-2016-B	Seam slippage resistance (mm) 1,70 EN ISO 13936/2:2004 2,00  Abrasion resistance (Fully worn off) 60.000 EN ISO 12947-2:1998  Abrasion resistance (change of aspect: 3000 cycles) 4-5 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)  Pilling resistance 4-5 EN ISO 12945/2:2000  Lightfastness 5-6 EN ISO 105-B02:1998 & 105 B02/A01:2002 	Soiling and cleanability 4-5 FORD FLTM BN 112-08:2005  - Spot-cleaning with soap and water - No chemicals needed for cleaning - Machine-washable  Washing conditions  Dimensional change domestic washing and drying (%) -2,00% EN ISO 3759:2008, EN ISO 6330:2000, EN ISO 5077:2008 	BS5852 Source 0 ✓ BS5852 Source 1 ✓ EN1021-Part 1:2006 ✓ EN1021-Part 2:2006 ✓ CAL TB 117:2013 ✓ NFPA 260:2013 ✓ BS 7176 Low Hazard ✓ UNI 9175 Clase 3IM ✓	Environmental composition  • Recycled yarn 27% • GRS Recycled PET bottles 12% • GRS Recycled CO waste 15% • Standard yarn 73% • Low-impact yarn (PP) 30% • PES yarn 24% • MA yarn 19% Sustainability - Oekotex certified - REACH approved chemicals and dyes - Biocide and PFCs free - Zero-waste production - Manufactured under ISO 9001 and ISO 14001 standards - Made in Barcelona (EU)