crevin

Galaxy

wool

Characteristics

Total composition

58%WO 19%PP 17%PES 6%CO



Width

138 + 4cm

Weight

605 gr/m² ± 5 %
835 gr/lm ± 5 %

Custom code

UE: 5112.20.00
USA: 5112.20.10.00

Laboratory test number

Document 13691, 13692, 13693, 13694, 13695
WYS 95102
2018AN0583

Specifications

Seam slippage resistance (mm) 2,00 / 2,00
EN ISO 13936/2:2004



Abrasion resistance (End point) 35.000
EN ISO 12947-2:1998



Abrasion resistance (change of aspect: 3000 cycles) 4
EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)

Pilling resistance 5
EN ISO 12945/2:2000

Lightfastness 5-6
EN ISO 105-B02:1998 & 105 B02/A01:2002



Colour fastness to rubbing 4-5 / 5
EN ISO 105-X12:2002



Care

Washing conditions



Notes

Domestic machine wash with special wool program.
Tumble dry on a low cycle.
Dry horizontally.
Iron only on the reverse side using a protective cloth between fabric and iron at minimum iron temperature.

Dimensional change domestic washing and drying (%) -3,00% / -3,00%
EN ISO 3759:2008, EN ISO 6330:2000, EN ISO 5077:2008



Ignitability

BS5852 Source 0	✓
BS5852 Source 1	✓
EN1021-Part 1:2006	✓
EN1021-Part 2:2006	✓
CAL TB 117:2013	✓
NFPA 260:2013	✓
BS 7176 Low Hazard	✓
UNI 9175 Clase 3IM	✓

Notes

Slight colour variations may occur from batch to batch.
Raport design 53,4cm x 31,4cm +/-3,5%

Attention

When confectioning or washing a sofa cover with velcro, attach a protective strip to avoid damage to the fabric.

Environment

Environmental composition



- Recycled yarn 23%
  - GRS Recycled PET bottles 17%
  - Circular yarn from own waste 3%
  - GRS Recycled CO waste 3%
- Standard yarn 77%
  - Low-impact yarn (PP) 19%
  - WO yarn 58%

Sustainability

- Oekotex certified
- REACH approved chemicals and dyes
- Biocide and PFCs free
- Zero-waste production
- Manufactured under ISO 9001 and ISO 14001 standards
- Made in Barcelona (EU)

AENOR QUALITY MANAGEMENT ISO 9001 · AENOR ENVIRONMENTAL MANAGEMENT ISO 14001 · REACH COMPLIANT · OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 20200K0217 AITEX

Results that are underlined have been obtained by Crevin's internal laboratory and must therefore be seen as indicative.