





















Characteristics 	Specifications 	Care 	Ignitability 	Environment 
<p>Total composition 80%PP 18%PES 2%PU</p>  <p>Width 140 + 4cm</p> <p>Weight 764 gr/m² ± 5 % 1070 gr/lm ± 5 %</p> <p>Custom code UE: 5903.20.90 USA: 5903.20.18.00</p> <p>Laboratory test number IN-00261-2017</p>	<p>Seam slippage resistance (mm) <u>2,00</u> EN ISO 13936/2:2004 3,00</p>  <p>Abrasion resistance (End point) >100.000 EN ISO 12947-2:1998</p>  <p>Pilling resistance 5 EN ISO 12945/2:2000</p>  <p>Lightfastness to weather ≥6 EN ISO 105-B04:1997 (1000 hours)</p>  <p>Colour fastness to rubbing 4-5 EN ISO 105-X12:2002 4-5</p>  <p>Colour fastness to domestic and commercial laundering (30°) 4-5 EN ISO 105-C06:1997/AC:2009</p>  <p>Water repellency (Hydrophobia) >2000mbar (20 mtrs) AATCC 79:2000</p>  <p>Resistance to putrefaction (Mould & bacterium resist.) YES EN 20811:1992 - AATCC 30:2004</p>	<p>Cleanability</p> <ul style="list-style-type: none"> Spot-cleaning with soap and water No chemicals needed for cleaning Machine-washable  <p>Washing conditions</p>  <p>Notes Bleach cleanable 80% water 20% bleach. In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40°C during at least 30 minutes. Use gentle cycle with minimal centrifugation.</p> <p>Dimensional change domestic washing and drying (%) -3,00% -1,00% EN ISO 3759:2008, EN ISO 6330:2000, EN ISO 5077:2008</p>  <p>Urine fastness 4-5 EN ISO 105-E01:1996</p>  <p>Swimming pool chlorine fastness 4-5 EN ISO 105-E03:1993</p>  <p>Sea water fastness 4-5 EN ISO 105-E02:1996</p> 	<p>BS5852 Source 0 ✓ BS5852 Source 1 ✓ EN1021-Part 1:2006 ✓ EN1021-Part 2:2006 ✓ CAL TB 117:2013 ✓ NFPA 260:2013 ✓ BS 7176 Low Hazard UPON REQUEST UNI 9175 Clase 3IM UPON REQUEST IMO Anexo 1 Parte 8 ✓</p> <p>Notes Recommendation: Distance overlock and stitch: 12 mm + 0,5 mm minimum Needle thickness: 110 Nm Thread: Polyester - Cotton 74 Tex (n°36) Stitch density: 4.0 stitches+0,1 stitches/cm</p> <p>Attention When confectioning or washing the sofa cover with velcro please attach a protective cloth.</p>	<p>Environmental composition</p>  <p>Recycled yarn 18%</p> <ul style="list-style-type: none"> GRS Recycled PET bottles 18% Standard yarn 82% Low-impact yarn (PP) 82% <p>Sustainability</p> <ul style="list-style-type: none"> Oekotex certified REACH approved chemicals and dyes Biocide and PFCs free Zero-waste production Manufactured under ISO 9001 and ISO 14001 standards Made in Barcelona (EU) 