





















Characteristics 	Specifications 	Care 	Ignitability 	Environment 
<p>Total composition 82%PP 18%PES</p>  <p>Width 140 + 4cm</p> <p>Weight 750 gr/m² ± 5 % 1050 gr/lm ± 5 %</p> <p>Custom code UE: 5407.73.00 USA: 5407.73.20.60</p> <p>Laboratory test number IN-00261-2017 AN0584 WYS85789</p>	<p>Seam slippage resistance (mm) <u>2,00</u> EN ISO 13936/2:2004 3,00</p>  <p>Abrasion resistance (End point) <u>>100.000</u> EN ISO 12947-2:1998</p>  <p>Pilling resistance <u>5</u> EN ISO 12945/2:2000</p>  <p>Lightfastness to weather <u>≥6</u> EN ISO 105-B04:1997 (1000 hours)</p>  <p>Colour fastness to rubbing <u>4-5</u> EN ISO 105-X12:2002 4-5</p>  <p>Colour fastness to domestic and commercial laundering (30°) <u>4-5</u> EN ISO 105-C06:1997/AC:2009</p>  <p>Water repellency (Hydrophobia) <u>>2000mbar (20 mtrs)</u> AATCC 79:2000</p>  <p>Urine fastness <u>4-5</u> EN ISO 105-E01:1996</p> 	<p>Cleanability</p> <ul style="list-style-type: none"> Spot-cleaning with soap and water No chemicals needed for cleaning Machine-washable  <p>Washing conditions</p>  <p>Notes Bleach cleanable 80% water 20% bleach. In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40°C during at least 30 minutes. Use gentle cycle with minimal centrifugation.</p> <p>Dimensional change domestic washing and drying (%) <u>-3,00%</u> <u>-1,00%</u> EN ISO 3759:2008, EN ISO 6330:2000, EN ISO 5077:2008</p>  <p>Swimming pool chlorine fastness <u>4-5</u> EN ISO 105-E03:1993</p>  <p>Sea water fastness <u>4-5</u> EN ISO 105-E02:1996</p> 	<p>BS5852 Source 0 ✓ BS5852 Source 1 ✓ EN1021-Part 1:2006 ✓ EN1021-Part 2:2006 ✓ CAL TB 117:2013 ✓ NFPA 260:2013 ✓ BS 7176 Low Hazard UPON REQUEST ✓ UNI 9175 Clase 3IM UPON REQUEST ✓ IMO Anexo 1 Parte 8 ✓</p> <p>Notes Recommendation: Distance overlock and stitch: 12 mm + 0,5 mm minimum Needle thickness: 110 Nm Thread: Polyester - Cotton 74 Tex (n°36) Stitch density: 4.0 stitches+0,1 stitches/cm</p> <p>Attention When confectioning or washing the sofa cover with velcro please attach a protective cloth.</p>	<p>Environmental composition</p>  <p>18% = 6 bottles</p> <ul style="list-style-type: none"> Recycled yarn 18% <ul style="list-style-type: none"> GRS Recycled PET bottles 18% Standard yarn 82% <ul style="list-style-type: none"> Low-impact yarn (PP) 82% <p>Sustainability</p> <ul style="list-style-type: none"> Oekotex certified REACH approved chemicals and dyes Biocide and PFCs free Zero-waste production Manufactured under ISO 9001 and ISO 14001 standards Made in Barcelona (EU) 