









crevin

Dolce (Imp)

outdoor • bleach cleanable • stain resistant • washable

Characteristics 	Specifications 	Care 	Ignitability 	Environment 
<p>Total composition 57%PP 38%PES 5%PU</p>  <p>Width 140 + 4cm</p> <p>Weight 390 gr/m² ± 5 % 546 gr/lm ± 5 %</p> <p>Custom code UE: 5903.20.90 USA: 5903.20.18.00</p> <p>Laboratory test number IN-01025/2014 IN-00357/2010</p>	<p>Seam slippage resistance (mm) 1,90 EN ISO 13936/2:2004 WARP: 0-4 scale, value at 1.90 WEFT: 0-4 scale, value at 2.20</p> <p>Abrasion resistance (End point) 60.000 EN ISO 12947-2:1998 0-100,000 scale, value at 60,000</p> <p>Abrasion resistance (change of aspect: 3000 cycles) 4-5 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) 0-5 scale, value between 4 and 5</p> <p>Pilling resistance 4-5 EN ISO 12945/2:2000 0-5 scale, value between 4 and 5</p> <p>Lightfastness to weather >6 EN ISO 105-B04:1997 (1000 hours) 0-8 scale, value at 6</p> <p>Colour fastness to rubbing 4-5 EN ISO 105-X12:2002 DRY: 0-5 scale, value between 4 and 5 WET: 0-5 scale, value between 4 and 5</p> <p>Resistance to water penetration >2000mbar 0-2000 scale, value at 2000</p> <p>Resistance to putrefaction (Mould & bacterium resist.) Face fabric</p> <p>Swimming pool chlorine fastness 4-5 EN ISO 105-E03:1993 0-5 scale, value between 4 and 5</p>	<p>Soiling and cleanability 4 FORD FLTM BN 112-08:2005 0-5 scale, value at 4</p> <ul style="list-style-type: none"> Permanent protection against stains Spot-cleaning with soap and water No chemicals needed for cleaning Machine-washable  <p>Washing conditions 40, triangle, crossed square, crossed circle</p> <p>Notes Bleach cleanable 80% water 20% bleach. In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40 °C during at least 30 minutes. Use gentle cycle with minimal centrifugation.</p> <p>Dimensional change domestic washing and drying (%) -2,00% EN ISO 3759:2008, EN ISO 6330:2000, EN ISO 5077:2008 WARP: -3 to +3 scale, value at -2 WEFT: -3 to +3 scale, value at -2</p> <p>Sea water fastness 4-5 EN ISO 105-E02:1996 0-5 scale, value between 4 and 5</p> <p>Urine fastness 4-5 EN ISO 105-E01:1996 0-5 scale, value between 4 and 5</p>	<p>BS5852 Source 0 ✓</p> <p>BS5852 Source 1 UPON REQUEST</p> <p>EN1021-Part 1:2006 ✓</p> <p>EN1021-Part 2:2006 UPON REQUEST</p> <p>CAL TB 117:2013 ✓</p> <p>NFPA 260:2013 ✓</p> <p>BS 7176 Low Hazard UPON REQUEST</p> <p>UNI 9175 Clase 3IM UPON REQUEST</p> <p>IMO Anexo 1 Parte 8 UPON REQUEST</p> <p>Notes STAIN REPELLENCE PROTECTION</p> <p>Attention When confectioning or washing the sofa cover with velcro please attach a protective cloth.</p>	<p>Environmental composition</p>  <p>Recycled yarn 40%</p> <ul style="list-style-type: none"> GRS Recycled PET bottles 40% Standard yarn 60% Low-impact yarn (PP) 60% <p>Sustainability</p> <ul style="list-style-type: none"> Oekotex certified REACH approved chemicals and dyes Biocide and PFCs free Zero-waste production Manufactured under ISO 9001 and ISO 14001 standards Made in Barcelona (EU) 