



5 years guarantee • fire resistant

General Information	Specifications	Care										
 <p>Composition 47%PES 23%PP 17%MA 13%CO</p> <p>Width 140 + 4cm</p> <p>Weight 479 gr/m² ± 5 % 670 gr/lm ± 5 %</p> <p>Custom code UE: 5801.36.00 USA: 5801.36.00.20</p> <p>Laboratory test number IN-00680-2017-B-1 IN-01415-2015 IN-00680/2017-B-1 87019</p>	<p>Seam slippage resistance (mm) Warp: 3,80 Weft: 3,90 EN ISO 13936/2:2004</p> <p>Abrasion resistance (End point) 50.000 EN ISO 12947-2:1998</p> <p>Abrasion resistance (change of aspect: 3000 cycles) 4-5 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)</p> <p>Pilling resistance 4-5 EN ISO 12945/2:2000</p> <p>Lightfastness 6-7 EN ISO 105-B02:1998 and 105 B02/A01:2002</p> <p>Colour fastness to rubbing Dry: 4-5 Wet: 4-5 EN ISO 105-X12:2002</p> <p>Colour fastness to domestic and comercial laundering (30°) 4-5 EN ISO 105-C06:1997/AC:2009</p> <p>Notes: Distance overlock and stitch: 12 mm + 0,5 mm minimum Needle thickness: 110 Nm Thread: Polyester - Cotton 74 Tex (n°36) Stitch density: 4.0 stitches+0,1 stitches/cm</p>	<p>PERFORMANCE+ Easy to clean, longlasting fabrics</p> <p>Washing conditions </p> <p>Soiling and cleanability 4 FORD FLTM BN 112-08:2005</p> <p>Dimensional change domestic washing and drying (%) Warp: -2 Weft: -1,5 EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008</p> <p>When confectioning or washing the sofa cover with velcro please attach a protective cloth.</p> <p>Ignitability</p> <table border="0"> <tr> <td>BS5852 Source 0</td> <td>EN1021-Part 2:2006</td> </tr> <tr> <td>EN1021-Part 1:2006</td> <td>BS 7176 Low Hazard</td> </tr> <tr> <td>CAL TB 117:2013</td> <td>UNI 9175 Clase 3IM</td> </tr> <tr> <td>NFPA 260:2013</td> <td>IMO Anexo 1 Parte 8</td> </tr> <tr> <td>BS5852 Source 1</td> <td></td> </tr> </table>	BS5852 Source 0	EN1021-Part 2:2006	EN1021-Part 1:2006	BS 7176 Low Hazard	CAL TB 117:2013	UNI 9175 Clase 3IM	NFPA 260:2013	IMO Anexo 1 Parte 8	BS5852 Source 1	
BS5852 Source 0	EN1021-Part 2:2006											
EN1021-Part 1:2006	BS 7176 Low Hazard											
CAL TB 117:2013	UNI 9175 Clase 3IM											
NFPA 260:2013	IMO Anexo 1 Parte 8											
BS5852 Source 1												

Environmental considerations

 <p>26% recycled yarn</p> <p>13% GRS recycled PET bottles 13% Recycled CO 23% Low impact yarn (PP) 34% PES 17% MA</p>	<p>Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.</p> <p>Carbon footprint <i>In process</i> kg CO₂ eq / m</p> <p>Water consumption <i>In process</i> liters / m</p>	 <p>UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa</p> <p>Study realized in collaboration with UPC</p> <p>Methodology: Life Cycle Analysis. ISO 14040 standard.</p> <p>Database: Own data, Ecoinvent 3.6 database and published data.</p> <p>Functional unit: 1 linear meters, 140 cm width.</p> <p>Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03</p>
---	--	---

Designed and Crafted in Terrassa (Barcelona)

Certificates

