## Velvety-Fr

# crevin

## 5 years guarantee • fire resistant

#### General Information **Specifications** Care **PERFORMANCE+** Seam slippage resistance (mm) Easy to clean, longlasting fabrics Warp: 1,00 / Weft: 1,00 Washing conditions Abrasion resistance (End point) 200.000 EN ISO 12947-2:1998 Abrasion resistance Soiling and cleanability 4-5 FORD FLTM BN 112-08:2005 (change of aspect: 3000 cycles) 4-5 FN ISO 12947/4:1998 and EN 14465:2003 (Annex A) **Dimensional change domestic** washing and drying (%) Warp: <u>-1,6</u> **Pilling resistance** 5 EN ISO 12945/2:2000 Weft: -2 Lightfastness 5-6 EN ISO 105-B02:1998 Iron on reverse side. When confectioning or washing the sofa cover with velcro please attach a protective cloth. Composition Colour fastness to rubbing 74%PES 12%PES REC 7%CO REC 7%MA Dry: 5 / Wet: 4-5 EN ISO 105-X12:2002 Width 140 + 4cm Snagging resistance\* 4-5 ASTM D 3939:13(2017) Weight \* In a snagging test, a fabric sample is placed on a cylindrical drum $571 \, \text{gr/m2} \pm 5 \, \%$ and a spiked ball bounces randomly against the rotating fabric. 800 gr/lm ± 5 % After 600 cycles the degree of damage is graded on a scale of 1 to 5. A 4-5 grading stands for very high snag resistance. In practice, Ignitability this means that no snags or threading are likely to occur, although Custom code prolonged and intense animal impact may provoke superficial UE: 5801.36.00 pilling, which can be easily removed by simple brushing. USA: 5801.36.00.20 EN1021-Part 2:2006 BS5852 Source 0 Caution: Scratching is natural feline behaviour: A 4-5 grading does EN1021-Part 1:2006 BS 7176 Low Hazard not mean a fabric is immune to the impact of animal claws. To protect upholstered furniture from prolonged and severe scratching, CAL TB 117:2013 UNI 9175 Clase 3IM Laboratory test number especially from cats, alternative scratching posts or protective Document 13868, 13865, 13884, 13883 NFPA 260:2013 IMO Anexo 1 Parte 8 pads are recommended. Destructive scratching due to extreme BS5852 Source 1 Entry 101094, -01, -02 feline behaviour is no ground for claims. **Environmental considerations**

# recycled var 12% GRS recycled PET bottles 8% Recycled CO 74% **PES** 7% MA

**Designed and Crafted** in Terrassa (Barcelona)

### Life cycle analysis

Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

### **Carbon footprint**



#### Water consumption



### Certificates



#### UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH

Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology: Life Cycle Analysis. ISO 14040 standard.

Database: Own data, Ecoinvent 3.6 database and published data.

Functional unit: 1 linear meters, 140 cm width.

Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03



Rev. nº: 9 - 28/04/2023 \*Results have been obtained by Crevin's internal laboratory and must therefore be seen as indicative.