Hatch

# crevin

# 5 years guarantee

## General Information



Composition 77%PP 23%PES REC

Width 140 + 4cm

Weight

 $586 \, \text{gr/m2} \pm 5 \, \%$  $820 \, \text{gr/lm} \pm 5 \, \%$ 

**Custom code** UE: 5407.73.00 USA: 5407.73.20.60

Laboratory test number 4858-004T\_1\_EN 4858-003T\_1A\_EN

## **Specifications**

Seam slippage resistance (mm)

Warp: 2,10 Weft: 1,20

EN ISO 13936/2:2004

Abrasion resistance (End point)

26.667 EN ISO 12947-2:1998

Pilling resistance

4 EN ISO 12945/2:2000

Lightfastness

5 EN ISO 105-B02:1998

Colour fastness to rubbing

Dry: 4-5 Wet: 4-5

EN ISO 105-X12:2002

#### Care

#### **PERFORMANCE+**

Easy to clean, longlasting fabrics

Washing conditions









Soiling and cleanability

4-5 FORD FLTM BN 112-08:2005


When confectioning or washing the sofa cover with velcro please attach a protective cloth.

# **Ignitability**

BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013

BS5852 Source 1 EN1021-Part 2:2006 UNI 9175 Clase 3IM

#### **Environmental considerations**



23% GRS recycled PET bottles 77% Low impact yarn (PP)

#### Life cycle analysis

Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

**Carbon footprint** 

 $3,83 \frac{\text{kg CO}_2 \text{eq/m}}{\text{-}}$ 

Water consumption

78,69 liters/m



UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH

Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology: Life Cycle Analysis. ISO 14040 standard.

Own data, Ecoinvent 3.6 database and published data.

1 linear meters, 140 cm width.

Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03

Designed and Crafted in Terrassa (Barcelona)

Certificates











